

253- Acrylic PVA Matt

PRODUCT DESCRIPTION AND USES

Protective PVA Matt is designed on a vinyl acrylic co-polymer. This product is an ideal finish over most surface areas where a matt finish is required. Normally not recommended for exterior use. Do not use in kitchens, bathrooms, or in any wet areas.

PHYSICAL PROPERTIES

Colour/Texture	White, but can be tinted/flat matt
Drying Time	15 - 20 minutes in ambient conditions
Recoat Time	Allow at least 1 hour between coats in ambient conditions.

SURFACE PREPARATION

Surface must be free from dirt, mould, loose and flaking paint, and grease. Mould should be treated with an anti-mould sterilising solution. Surfaces previously painted with a gloss should be sanded back to a matt surface. New work should be primed with Protective Acrylic Primer Sealer to ensure a good "key" is attained on the surface, followed by two finish coats of PVA Matt to give the best protection and depth of colour.

APPLICATION DATA

PVA Matt can be applied by brush, roller or spray. Stir product thoroughly prior to application. Do not use when surface temperature of substrate is below 10°C.

Theoretical Spreading Rate	Between 7-9m ² /litre depending on the porosity of surface
Thinners	Thin the product sparingly with clean water if necessary Soak equipment in clean water during breaks Clean all equipment with clean water immediately after use

TRANSPORTATION AND DISPOSAL

Hazchem not regulated.

OTHER INFORMATION

If the surface you propose to paint is not referred to, contact Protective Paints Technical Department for classification.

For further technical information please phone 0800 724 684.

RELIABILITY OF INFORMATION

All statements and technical information contained herein are based on tests we believe to be reliable but the accuracy thereof is not guaranteed. Since Protective Paints Ltd has no control over product application, purchasers and users must confirm the suitability of our products under their conditions to meet their own requirements.

ISSUE NUMBER: 253- (V2)
ISSUE DATE: 21 August 2013