

248-290

Portco Trade Contact Adhesive

PRODUCT DESCRIPTION AND USES

Portco Trade Contact Adhesive is a water based natural latex contact adhesive specially designed to bond pre-glued cork tiles to most concrete and timber substrates. Portco Trade Contact Adhesive is used in conjunction with 249-323 Neoprene Primer. If in doubt regarding the suitability of a substrate, contact Protective Paints Technical department.

Typical Uses

- Pre-glued cork tiles

Typical Substrate

- Concrete - Porous
- Cement Board
- Hard Board
- Timber

Properties

- Easy to apply
 - Rapid installation of cork tiles
 - Excellent bonding
 - Non flammable
-

PHYSICAL PROPERTIES

| | |
|-------------|---------------------------------------|
| Colour | White |
| Solids | 53% ± 1% |
| Solvent | Water |
| Drying Time | 30-60 minutes in ambient temperatures |
| Packaging | 1L, 4L, 10L, 20L |

SHELF LIFE

Twelve months from date of manufacture in unopened containers @ 20°C. Portco Trade Contact Adhesive should not be returned to the container.

SURFACE PREPARATION

All surfaces must be dry, clean, smooth and free from hydrostatic pressure, capillary action, grease, oil, wax, dust and other contaminants. All surfaces should be primed with 249-323 Neoprene Primer. (Refer specification sheet for full details).

Timber floors must be well ventilated under floor.

Uneven or damaged floors should be repaired with cementitious levelling compound.

Concrete floors must be at least 50-60 days old to avoid excessive moisture content affecting the parquetry. Refer technical note 17

- Testing for Moisture Content to identify suitability for coating.

APPLICATION EQUIPMENT

Portco Trade Contact Adhesive can be applied using a 6mm mohair roller or conventional spray equipment.

APPLICATION DATA

| | |
|----------------------------|---|
| Recommended No. of Coats | 1 |
| Theoretical Spreading Rate | 6m ² /litre (dependant on porosity of substrate) |
| Thinners | Clean water |
| Clean up | Warm soapy water |

THINNING

Portco Trade Contact Adhesive is supplied ready for use and therefore should not require thinning. Where the product has begun to thicken, approximately 5% clean water can be added to ease viscosity.

APPLICATION METHOD

Stir Portco Trade Contact Adhesive prior to use.

Apply an even coat of Portco Trade Contact Adhesive to primed substrate and allow to dry (30-60 minutes).

Apply pre-glued cork tiles (refer Technical note 8- laying cork tiles).

NOTES

Do not apply Portco Trade Contact Adhesive when temperature or substrate is below 10°C or above 35°C. Ensure Portco Trade Contact Adhesive is used in a well ventilated area. Ensure a dust mask is worn whilst sanding floor.

HEALTH AND SAFETY

Irritant

Avoid contact with skin and eyes. Avoid breathing vapour or sanding dust. When using this product it is recommended that full overalls, gloves, face mask and goggles be worn. Store container in a safe place when not in use. Do not burn container.

FIRST AID

EYES

Flush with water for at least 15 minutes and seek medical advice.

SKIN

Wash contact areas with soap and water. Remove all contaminated clothing, and seek medical advice. Do not scrub.

INHALATION

Remove patient from further exposure, and keep patient warm and comfortable.

INGESTION

Do not induce vomiting. Rinse mouth with water. Seek medical advice as soon as possible.

TRANSPORTATION AND DISPOSAL

Not Hazno regulated.

OTHER INFORMATION

This product may be used for a wide variety of surfaces. If the surface you propose to paint is not referred to, contact Protective Paints Technical Department for classification.

For further technical information please phone 0800 724 684.

RELIABILITY OF INFORMATION

All statements and technical information contained herein are based on tests we believe to be reliable but the accuracy thereof is not guaranteed. Since Protective Paints Ltd has no control over product application, purchasers and users must confirm the suitability of our products under their conditions to meet their own requirements.

ISSUE NUMBER: 248-290 (V3)

ISSUE DATE: 21 March 2017

bwjb